

wherein the exterior surface layer has the thickness of 1 to 5 micro-meters.

42. The photosensitive member of claim 34,

wherein the tantalum doped tin oxide is surface-treated by a silane coupling agent or a titanium coupling agent.--.


REMARKS

The above preliminary amendment is necessary to add new claims and to incorporate the amendments that were made during prosecution in the parent application Serial No. 08/693,717. An Annex is attached herewith which includes clean copies of the paragraphs and claims as amended.

Entry of this amendment is respectfully requested.

Respectfully submitted,

MCDERMOTT WILL & EMERY


Edward J. Wise
Registration No. 34,523

600 13th Street, N.W.
Washington, DC 20005-3096
(202) 756-8000 EJW:BD
Date: September 19, 2001
Facsimile: (202) 756-8087

**ANNEX INCLUDING CLEAN VERSION OF AMENDED PARAGRAPHS
OF SPECIFICATION AND CLAIMS**

IN THE SPECIFICATION:

Please replace the paragraph beginning at line 2 on page 5 with the following:

An object of the present invention is to utilize the aforesaid information to provide a novel layer containing conductive tantalum doped tin oxide powder, which is nontoxic and possesses excellent stability as a layer formed between a substrate and a photosensitive layer of a photosensitive member and/or as a protective layer for a photosensitive layer of a photosensitive member.

Please replace the paragraph beginning at line 10 on page 24 with the following:

A photosensitive member was produced in exactly the same way as Example 1 with the exception that carbon black was substituted for the tantalum-doped tin oxide powder used in the conductive layer in Example 1.

IN THE CLAIMS:

Please replace claims 15 and 18-21 as follows:

15. The photosensitive member of claim 13,
wherein the tantalum doped tin oxide is a tin oxide doped with 0.1 to 10 percentage-by-weight tantalum .
18. The photosensitive member of claim 13,
wherein the tantalum doped tin oxide has a mean particle size of less than 2 micrometers.
19. The photosensitive member of claim 18,
wherein the tantalum doped tin oxide has the mean particle size of 0.3 to 1.0 micrometers.
20. The photosensitive member of claim 13,

wherein a content of the tantalum doped tin oxide is 5 to 70 percentage-by-weight of the total of the exterior surface layer.

21. The photosensitive member of claim 13,

wherein the exterior surface layer has a thickness of 7 micro-meters or less.

T06T60" 0E05560